

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 948 956 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
13.10.1999 Bulletin 1999/41

(51) Int Cl.⁶: **A61K 6/083**

(21) Application number: **99106331.4**

(22) Date of filing: **26.03.1999**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **27.03.1998 US 79777 P**

(71) Applicant: **DENTSPLY DETREY GmbH
D-63303 Dreieich (DE)**





(72) Inventors:
• **Klee, Joachim E., Dr.
78315 Radolfzell (DE)**

• **Walz, Uwe
78467 Konstanz (DE)**
• **Lu, Kawang
Dover, DE 19901 (US)**

(74) Representative: **Hartz, Nikolai F., Dr. et al
Wächtershäuser & Hartz,
Patentanwälte,
Tal 29
80331 München (DE)**

(54) **Self-curing dental adhesive**

(57) A self-curing dental adhesive has at least one polymerizable resin; at least one polymerizable monomer; at least one polymerizable monomer with an acidic moiety selected from the group



and salts thereof; a stabilizer; an organic solvent or water in a content of from about 10 to about 90 percent by weight; and, at least one part of a thermal redox initiator system or a photoinitiator. The adhesive polymerizes immediately after application of a self-curing dental material that comprises a redox-initiator system, and has an adhesion to dentine of at least about 7 MPa.

EP 0 948 956 A2

Description**Technical Field**

- 5 [0001] The invention concerns a self-curing dental adhesive, which polymerizes after application of a self-curing dental restorative material that comprises a metal-based redox-initiator system without mixing of both systems.

Background of the Invention

- 10 [0002] Presently, the dental treatment of cavities of the teeth usually includes using dental composites, compomers or glass ionomers. The use of dental composites and compomers is connected with the application of the adhesive technique. Commonly, both adhesive and dental restorative materials are cured by irradiation with visible light. Dental composites have numerous advantages: high mechanical strength, excellent esthetic properties and a high abrasion resistance. These positive properties are complemented by the fluoride releasing properties of compomers.

- 15 [0003] The use of glass ionomers is advantageous at least in part because they are self-adhesive, biocompatible and usable without requiring irradiation by light. Furthermore, they can release fluoride ions. Otherwise, glass ionomers have a relatively low flexural strength and a high abrasion.

[0004] In order to develop a self-curing restorative material with improved mechanical properties, high abrasion resistance and fluoride release a thermal setting adhesive is required.

- 20 [0005] Recently, a dual-curing adhesive comprising sulfinates and champhor quinone/amines as polymerization initiator was developed by Dentsply Caulk, Milford DE.

[0006] Generally, a self-curing material is composed of at least of two components, due to the fact that the parts of the initiator system must be distributed in these components.

Summary of the Invention

[0007] It is an object of the present invention to provide a dental adhesive material.

[0008] It is another object of the invention to provide such a material that is self-curing.

- 30 [0009] These and other objects of the invention which shall become apparent from the present discussion and the following specification are accomplished by the invention as hereinafter described and claimed.

[0010] In general, a self-curing dental adhesive, comprises:

- 35 (i) at least a polymerizable resin
(ii) at least a polymerizable monomer
(iii) at least a polymerizable monomer with an acidic moiety selected from the group consisting of:




and salts thereof

- 45 (iv) at least a stabilizer,
(v) at least an organic solvent or water in a content of 10 to 90 percent weight of the adhesive and,
(vi) at least one part of a thermal redox initiator system or a photoinitiator,

wherein the dental adhesive is polymerizable immediately after application of a self-curing dental material that comprises a redox-initiator system, and wherein the dental adhesive has an adhesion to dentine of at least about 7 MPa.

Preferred Embodiments for Carrying Out the Invention

55 [0011] The present invention includes a self-curing dental adhesive that comprises at least a polymerizable resin, a polymerizable monomer, a polymerizable monomer with at least an acidic moiety selected from the group



or salts thereof, a stabilizer, an organic solvent and/or water in a content of 10 to 90 percent, and at least one part of a thermal redox initiator system and/or a photoinitiator that polymerizes immediately after application of a self-curing dental material that comprises a redox-initiator system.

[0012] The adhesion of the invented self-curing adhesive is at least about 7 MPa, preferably 9 MPa, most preferably 11 MPa.

[0013] Preferably, the self-curing dental adhesive contains a salt of a metal or an organo-metalic compound, an amine or a peroxide. Usable metal salts or organo-metalic compounds are selected from the group consisting of copper, silver, cerium, iron, chromium, nickel, vanadium and manganese. Frequently, the metal containing compound is an acetate, salicylate, naphenoate, thiourea complex, acetylacetonate or ethylene tetramine acidic acid.

[0014] The preferred amines are alkyl aryl amines, dialkyl aryl amines, trialkyl amines or derivatives therefrom.

[0015] Preferred peroxides include for example, diacyl peroxides, peresters, perketales, peroxy dicarbonates, dialkyl peroxides, ketone peroxides or alkyl hydroxyperoxides, such as benzoylperoxide, 2,5-dimethyl-2,5-di(benzoylperoxy) hexane, tert.-butylamyl peroxide, di-(tert.-butyl) peroxide, cumenhydroperoxide, tert.-butylhydroperoxide, tert.-butylperoxy-(3,5,5-tri-methylhexanoate) and tert.-butylperoxy-2-ethylhexyl carbonate, laurylperoxide.

[0016] For example a dental adhesive comprising cupric acetylacetonate is applied in a cavity. The cavity is then filled by using a thermal setting material, that comprises cupric thiourea. Both materials polymerize together, whereby the self-curing restorative material also initiates the polymerization of the bonding material. The adhesion of this adhesive/restorative material is 9.0 ± 1.5 MPa.

Comparative Example 1

Dental adhesive

[0017] Equal amounts of Prime & Bond 2.1™ (Dentsply, De Trey, Constance) and the Self Cure Activator (Dentsply, Caulk, Milford DE) were mixed.

Self-curing dental restorative material

[0018] The used dental restorative material is composed of a powder and a liquid. These have the following composition:

Powder:

[0019] 50.3639 g silylated Strontium-alumo-silicate glass, 2.1546 g silylated Strontium-alumo-silicate glass comprising 2 wt-% cupric thiourea complex and 1.0773 g silylated Strontium-alumo-silicate glass containing 10 wt-% ascorbic acid were mixed homogeneously.

Liquid:

[0020] 18.0000 g of dipentaerythritolpentaacrylate monophosphate and 2-(dimethyl) aminoethyl methacrylate (AP-1) comprising 30 wt-% diethylene glycol dimethacrylate, 4.5000 g of macromonomer M-1 (synthesized by reaction of two mols of methacrylic acid, two mols of 2,2-bis-[4-(2,3-epoxypropoxy)-phenyl]-propane and one mole of adipic acid) comprising 30 wt-% diethylene glycol dimethacrylate), 10.6328 g of diethylene glycol dimethacrylate, 0.0167 g of N, N-bis(β-hydroxyethyl)-p-toluidine, 0.5049 g of tert.-butyl peroxy benzoate, 0.0113 g of 2,6-di-tert.-butyl-p-cresol were mixed homogeneously.

Application

[0021] Immediately before use the dental adhesive is applied. Thereafter the restorative material obtained by homogeneous mixture of powder and liquid, in the weight (wt.)-ratio 3.2:1.0, was applied. The working time is 3.75 minutes and the setting time is 3.00 minutes. The adhesion to dentine was measured to be 8.58 ± 1.32 MPa. The dental restorative material shows the following mechanical properties: compressive strength of 256.6 ± 11.9 MPa, a flexural

strength of 87.0 ± 3.4 and an E-modules of 7780 ± 785 MPa.

Example 1

Dental adhesive A

[0022] 3.2419 g of 7,7,9,63,63,65-hexamethyl-4,13,60,69-tetraoxo-3,14,19,24,29,34,39,44,49,54, 59,70-dodecane-oxa-5,12,61,68-tetraaza doheptaconta diyl -1,72- dimethacrylate (R 5621), 3.7406 g of dipentaerythrol pentaacrylate monophosphate, 8.2819 g of 2,7,7,9,15-pentamethyl-4,13-dioxo-3,14-diox-5,12-diaza-hexadecanediyl-1,16-dimethacrylate, 0.4417 g of bisphenol-A-dimethacrylat, 0.1496 g of cetylaminhydrofluorid, 0.0377 g of 2,6-di-tert.-butyl-p-cresol and 0.0330 g of cupric-II-acetylacetonate were dissolved in 59.9736 g of acetone.

Self-curing dental restorative material

[0023] The dental restorative material is composed of powder and liquid as described in comparative example 1.

Application

[0024] Immediately before use the dental adhesive is applied. Thereafter the restorative material obtained by homogeneous mixed of powder and liquid, in the wt.-ratio 3.2:1.0, was applied. The working time is 3.75 minutes and the setting time is 3.00 minutes. The adhesion to dentine was measured to be 9.0 ± 1.5 MPa. The dental restorative material shows the following mechanical properties: compressive strength of 256.6 ± 11.9 MPa, a flexural strength of 87.0 ± 3.4 and an E-modules of 7780 ± 785 MPa.

Example 2

Dental adhesive A

[0025] 4.7593 g dipentaerythrol pentaacrylate monophosphate, 7.7083 g 2,7,7,9,15-pentamethyl-4,13-dioxo-3,14-diox-5,12-diaza-hexadecanediyl-1,16-dimethacrylate, 2.2130 g of 7,7,9,63,63,65-hexamethyl-4,13,60,69-tetraoxo-3,14,19,24,29,34,39,44,49,54,59,70-dodecaneoxa-5,12,61,68-tetraaza doheptacontadiyl-1,72-dimethacrylate (R 5621), 1.3177 g trimethylolpropane triacrylate, 2.8213 g diethylene glycol dimethacrylate, 0.0997 g cuppric acetyl acetonate, 0.1922 g 2,6-di-tert.-butyl-p-cresol, 0.1922 g cetylaminhydrofluorid and 1.6952 g of a nanofiller (av. particle size 7 nm), were dissolved in 79.0011 g of acetone.

Self-curing dental restorative material

[0026] The dental restorative material is composed of powder and liquid as described in comparative example 1.

Application

[0027] Immediately before use the dental adhesive is applied. Thereafter the restorative material obtained by homogeneous mixed of powder and liquid, in the wt.-ratio 3.4:1.0, was applied. The working time is 3.25 minutes and the setting time is 3.00 minutes. The adhesion to dentine was measured to be 11.1 ± 1.8 MPa.

Example 3

Dental adhesive A

[0028] 4.7137 g dipentaerythrol pentaacrylate monophosphate, 7.6345 g 2,7,7,9,15-pentamethyl-4,13-dioxo-3,14-diox-5,12-diaza-hexadecanediyl-1,16-dimethacrylate, 2.1918 g of 7,7,9,63,63,65-hexamethyl-4,13,60,69-tetraoxo-3,14,19,24,29,34,39,44,49,54, 59,70-dodecaneoxa-5,12,61,68-tetraaza doheptacontadiyl-1,72-dimethacrylate (R 5621), 1.3051 g trimethylolpropane triacrylate, 2.7943 g diethylene glycol dimethacrylate, 1.0559 g p-dimethyl benzoic acid ethylester, 0.1904 g 2,6-di-tert.-butyl-p-cresol, 0.1904 g cetylaminhydrofluorid and 1.6790 g of a nanofiller (av. particle size 7 nm), were dissolved in 78.2450 g of acetone.

Self-curing dental restorative material

[0029] The dental restorative material is composed of powder and liquid as described in comparative example 1.

Application

[0030] Immediately before use the dental adhesive is applied. Thereafter the restorative material obtained by homogeneous mixed of powder and liquid, in the wt.-ratio 3.4:1.0, was applied. The working time is 3.25 minutes and the setting time is 3.00 minutes. The adhesion to dentine was measured to be 8.9 ± 2.6 MPa.

Example 4Dental adhesive A

[0031] 3.2419 g of 7,7,9,63,63,65-hexamethyl-4,13,60,69-tetraoxo-3,14,19,24,29,34,39,44,49,54, 59,70-dodecane-oxa-5,12,61,68-tetraaza doheptacontadiyl -1,72- dimethacrylate (R 5621), 3.7406 g of dipentaerythrol pentaacrylate monophosphate, 8.2819 g of 2,7,7,9,15-pentamethyl-4,13-dioxo-3,14-diox-5,12-diaza-hexadecanediyl-1,16-dimethacrylate, 0.4417 g of bisphenol-A-dimethacrylat, 0.1496 g of cetylaminhydrofluorid, 0.0377 g of 2,6-di-tert.-butyl-p-cresol and 0.2283 g of cupric-II-acetylacetonate were dissolved in 59.9736 g of acetone.

Self-curing dental restorative materialPowder:

[0032] 89.10 g silylated Strontium-alumo-silicate glass, 10-10 g OX-50 organic filler, 1.00 g Aerosil R-972, 0.02 g cupric acetylacetonate and 0.15 g ascorbyl palmitate were mixed homogeneously.

Liquid:

[0033] 10.00 g OEMA, 10.00 g dipentaerythrolpentaacrylate monophosphate, 30.00 g diethylene glycol dimethacrylate, 50.00 g 2,2-bis-[p-(2-hydroxy-3-methacryloyloxypropoxy)-phenyl]-propane, 2.00 g distilled water and 0.20 g tert.-butyl peroxy benzoate were mixed homogeneously.


[0034] Apply one coat of the primer to etched dentine, air dry. Triturate powder and liquid of the restorative in capsule at 3.75:1 ratio for 12 seconds. Apply the paste to dentine in a post. Let the assembly self cure at 37°C. Then stored in 37°C water for 24 hours. Test sheer bond strength on Instron. The average bond strength was 9.18 Mpa.

[0035] It is evident therefore, that the objects of a a self-curing dental adhesive are carried out by the invention as herein described. All possible aspects of the invention beyond the best mode have not been necessarily described, and the scope of the invention shall only be determined by the following claims.

Claims

1. A self-curing dental adhesive, comprising


- (i) at least one polymerizable resin;
- (ii) at least one polymerizable monomer;
- (iii) at least one polymerizable monomer with an acidic moiety selected from the group consisting of



- and salts thereof;
- (iv) a stabilizer;
- (v) an organic solvent or water in a content of from about 10 to about 90 percent; and,
- (vi) at least one part of a thermal redox initiator system or a photoinitiator;

wherein the adhesive polymerizes immediately after application of a self-curing dental material that comprises a redox-initiator system, and has an adhesion to dentine of at least about 7 MPa.

2. A self-curing dental adhesive of claim 1 having an adhesion to dentine of at about 11 MPa.
3. A self-curing dental adhesive of claim 1 wherein said thermal redox initiator system is a salt of a metal or an organo-metalic containing compound, an amine or a peroxide.
4. A self-curing dental adhesive of claim 3 wherein said metal of said metal containing compound is selected from the group consisting of copper, silver, cerium, iron, chromium, nickel, vanadium and manganese.
5. A self-curing dental adhesive of claim 3 wherein said metal containing compound is an acetate, salicylate, naphe-noate, thiourea complex, acetylacetonate or ethylene tetramine acidic acid.
6. A self-curing dental adhesive of claims 3 wherein said amine is is an alkyl aryl amine, a dialkyl aryl amine, a trialkyl amine or derivatives therefrom.
7. A self-curing dental adhesive of claims 3 wherein said peroxide is a diacyl peroxide, a perester, a perketale, a peroxy dicarbonate, a dialkyl peroxide, a ketone peroxide or a alkyl hydroxyperoxide.
8. A self-curing dental adhesive of claims 3 wherein said peroxide selected from benzoylperoxide, 2,5-dimethyl-2,5-di(benzoylperoxy)hexane, tert.-butylamyl peroxide, di-(tert.-butyl) peroxide, cumenhydoperoxide, tert.-butylhydroperoxide, tert.-butylperoxy-(3,5,5-tri-methylhexanoate) and tert.-butylperoxy-2-ethylhexyl carbonate, laurylperoxide.



(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 948 956 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
19.07.2000 Bulletin 2000/29

(51) Int Cl.7: **A61K 6/083**

(43) Date of publication A2:
13.10.1999 Bulletin 1999/41

(21) Application number: **99106331.4**

(22) Date of filing: **26.03.1999**

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

- Walz, Uwe
78467 Konstanz (DE)
- Lu, Kawang
Dover, DE 19901 (US)

(30) Priority: **27.03.1998 US 79777 P**





(71) Applicant: **DENTSPLY DETREY GmbH**
D-63303 Dreieich (DE)

(74) Representative: **Hartz, Nikolai F., Dr. et al**
Wächtershäuser & Hartz,
Patentanwälte,
Tal 29
80331 München (DE)

(72) Inventors:
• Klee, Joachim E., Dr.
78315 Radolfzell (DE)

(54) **Self-curing dental adhesive**

(57) A self-curing dental adhesive has at least one polymerizable resin; at least one polymerizable monomer; at least one polymerizable monomer with an acidic moiety selected from the group



and salts thereof; a stabilizer; an organic solvent or water in a content of from about 10 to about 90 percent by weight; and, at least one part of a thermal redox initiator system or a photoinitiator. The adhesive polymerizes immediately after application of a self-curing dental material that comprises a redox-initiator system, and has an adhesion to dentine of at least about 7 MPa.

EP 0 948 956 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 10 6331

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.5)
X	EP 0 218 248 A (MUEHLBAUER ERNST KG) 15 April 1987 (1987-04-15) * column 4, line 19 - line 56 * * column 15, line 50 - column 16, line 22 * * column 17, line 1 - line 26 * * column 17, line 50 - line 56 * * claims; examples *	1,3-8	A61K6/083
A	US 5 556 897 A (HONDA NARIMICHI ET AL) 17 September 1996 (1996-09-17) * column 2, line 32 - line 67 * * column 3, line 10 - line 35 * * column 3, line 53 - column 9, line 57 * * column 9, line 63 - column 10, line 13 * * column 11, line 11 - line 20 *	1-8	
A	EP 0 811 368 A (TOKUYAMA CORP) 10 December 1997 (1997-12-10) * page 5, line 4 - line 20 * * page 5, line 35 - page 6, line 36 *	1-8	TECHNICAL FIELDS SEARCHED (Int.Cl.5)
A	WO 96 19179 A (DENTSPLY INT INC) 27 June 1996 (1996-06-27) * page 13, paragraph 13 - page 17, paragraph 1 * * application examples 2-11 *	1-8	A61K
A	EP 0 712 621 A (HERAEUS KULZER GMBH) 22 May 1996 (1996-05-22) * page 3, line 8 - line 12 *	1	
A	GB 2 261 223 A (G C DENTAL IND CORP) 12 May 1993 (1993-05-12) * page 3, paragraph 2 - page 9, paragraph 3 *	1-8	
		-/--	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 23 May 2000	Examiner Cousins-Van Steen, G
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons A : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 02 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 10 6331

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.8)
P, X	WO 98 46198 A (MINNESOTA MINING & MFG) 22 October 1998 (1998-10-22) * page 1, line 16 - line 28 * * page 12, line 8 - line 11 * * page 12, line 17 - line 23 * * page 13, line 21 - page 14, line 18 * * page 17, line 3 *	1, 3-8	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 23 May 2000	Examiner Cousins-Van Steen, G
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03.82 (F04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 10 6331

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

23-05-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0218248 A	15-04-1987	DE 3536077 A	09-04-1987
		JP 2588702 B	12-03-1997
		JP 62149707 A	03-07-1987
		US 4806381 A	21-02-1989
US 5556897 A	17-09-1996	JP 6024928 A	01-02-1994
EP 0811368 A	10-12-1997	US 5866631 A	02-02-1999
		WO 9723191 A	03-07-1997
		JP 9227325 A	02-09-1997
WO 9619179 A	27-06-1996	AU 695605 B	20-08-1998
		AU 4425696 A	10-07-1996
		BR 9510062 A	02-06-1998
		CA 2202755 A	27-06-1996
		EP 0799016 A	08-10-1997
		JP 10511354 T	04-11-1998
		ZA 9510792 A	20-06-1996
EP 0712621 A	22-05-1996	DE 4441124 A	23-05-1996
		CA 2163166 A	19-05-1996
		CN 1129150 A	21-08-1996
		JP 8224535 A	03-09-1996
		US 5618372 A	08-04-1997
GB 2261223 A	12-05-1993	DE 4237391 A	13-05-1993
		JP 5186309 A	27-07-1993
		US 5290172 A	01-03-1994
WO 9846198 A	22-10-1998	US 5922786 A	13-07-1999
		AU 5179998 A	11-11-1998
		EP 0973482 A	26-01-2000

EPO FORM P459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82